

TOTAL FOAM N' BASE COAT888.702.9915
www.totalwall.com**Combination Base Coat & Foam Adhesive****AMERICA'S EIFS AND STUCCO COMPANY!**

Total Foam N' Base is a 100% acrylic emulsion blend that is designed to be mixed with Portland cement in a 1:1 ratio by weight.

Foam N' Base serves two functions:

1. It produces the adhesive that will bond rigid polystyrene insulation board to raw masonry, exterior gypsum, Dens Glass, and cement board, and

2. It produces the base coating that embeds the reinforcing fabric over the face of rigid polystyrene insulation.

Foam N' Base is also available as a Total Wall Journeyman Series product, which is formulated for enhanced workability and designed to help the experienced plasterer increase jobsite production.

**Features**

- 100% Acrylic Formula
- Mixes easily with Portland Cement
- Base Coat & Foam Adhesive
- Journeyman Series & Premium

Coverage

225-250 square feet per pail as a base coat.

120-140 square feet per pail as a base & adhesive when using Standard 4 Reinforcing Mesh.

Application

Mixing Instructions

Open a 5-gallon pail of Foam N' Base and mix with a low speed mixer until the product is homogeneous. Pour one half of the Foam N' Base pail contents (30 pounds) into a clean mixing pail. While mixing the half pail of Foam N' Base, slowly add 30 pounds of fresh, lump free Portland type I, II, or I-II cement (approximately 1/3 of a 94 pound bag of cement) to the pail.

Add up to 1 quart of clean water to adjust workability. Allow the mix to stand for about 5 minutes then re-mix for 1 minute. If necessary, add a small amount of water to adjust workability. Final consistency should be a creamy light and easily trowelable mixture.

For use as an Adhesive

The substrate must be firm, dry and free of loose debris and any substance that would interfere with bond. The substrate must conform to System specifications. The preferred method of adhesive application is to cover the entire back of the insulation board with adhesive mix using a 3/8" notched trowel. Immediately press the insulation board onto the substrate with firm, even pressure.

An alternate Ribbon and Dab method may also be used. Using a steel trowel, apply a 2" wide by 3/8" deep band of Foam N' Base and Adhesive mix around the perimeter of the rigid insulation board. Apply evenly spaced trowel length dabs, 3/8" thick of Foam N' Base and Adhesive mix to the center area of the insulation board. At least 1/3 of the area of the backside of the board should now be covered with Foam N' Base and Adhesive mix. Do not apply adhesive to the edges of the insulation.

For use as a Base Coat

The rigid insulation board should already be bonded to the substrate and have had time for the adhesive to gain strength. In addition, any backwrapping at system stops or protrusions using detail mesh should be completed. Prepare the rigid insulation board facing by sanding or rasping all joints and surface areas that need to be brought into plane. Measure and cut an area of Total Wall standard reinforcing mesh.

Apply Foam N' Base mix in a 1/16" thick butter coat over the face of the insulation board. Immediately embed the reinforcing mesh using a steel trowel. Work the mesh into the butter coat by starting at the center and troweling toward the edges. Avoid making wrinkles or tears in the mesh.

The final coating should be a smooth even finish, thick enough only to embed the mesh so that the mesh pattern is not visible. Consult Total Wall specifications for full instruction on all details.

Handling and Storage

Do not apply to frozen or saturated surfaces. Do not apply if precipitation is forecast within 8 hours of application. Do not

apply if the temperature cannot be maintained above 40F for 24 hours. Shelf life in closed containers is 12-18 months when stored at 50-100F. Keep containers sealed and under cover when not in use.

Maintenance

If damage occurs to an installed system, please contact Total Wall for information on repair.

Precautions

This product is an alkaline water based material. Do not ingest. Avoid contact with skin and eyes. In case of contact, flush with water. For contact with eyes, get immediate medical attention in addition to flushing. Wear safety glasses and protective clothing. Keep out of reach of children and pets.

Revised: 06/2020



888.702.9915 Phone
888.702.9916 Fax
www.totalwall.com

Technical Data

Appearance	Viscous, milky liquid
pH	Approx. 9.5
Density	11 lbs./gal.
Polymer type.....	100 % acrylic
Solvent system	Aqueous