

TOTAL LASTIC PREMIER

888.702.9915
www.totalwall.com

Premium Quality Elastomeric Coating

AMERICA'S EIFS AND STUCCO COMPANY!

Total Lastic Premier is our highest quality Elastomeric coating.

Total Lastic Premier can be applied directly to concrete, concrete block, EIFS finishes, wood, asbestos shingles and other surfaces with or without the use of a primer.

Total Lastic Premier provides a waterproof, attractive finish that has elasticity to bridge old and new cracks.

Total Lastic Premier has patented DPR for added mildew resistance and dirt pickup.

Total Lastic Premier is available in a smooth (non-textured) base, a fine texture (50 mesh) base, and medium (30 mesh) texture base.



Features

- Meets VOC, VOS requirements
- Permanent elasticity bridges cracks
- Does not create a vapor barrier
- Weather resistant
- Resists dirt, mildew / non-chalk-

Coverage

Coverage (smooth base)

Porous substrates	80-120 sq.ft./gal /coat
Non-porous substrates	120-150 sq.ft./gal/coat

Coverage (textured base)

Porous substrates	60-100 sq.ft./gal /coat
Non-porous substrates	100-130 sq.ft./gal/coat

Application

Prepare surface by removing any dirt, oils, loose debris or any substance that may interfere with the bond. A dry surface is preferable but a slightly damp surface is acceptable. Glossy surfaces should be lightly sanded prior to application.

It is advisable to fill any spalled or broken areas of substrate with a suitable patching material. Roll or brush over any cracks before coating the entire wall. Any cracks greater than 1/32" should be filled with a paintable grade acrylic or single component urethane caulk sealant and allow to cure 4 hours before beginning coating.

Stir product for one minute with a low speed mixer or manually stick-stir as desired. Do not beat excessive air into the product. Apply T-Wall Lastic Premier by roller, brush or airless sprayer.

For airless sprayer, use a reversible tip with a #35 orifice-spraying tip.

For roller application, a 3/4" nap roller produces good results. The nap thickness can be varied to compensate for the substrate characteristics and the desired appearance. Thin product with up to 5-ounces of water per gallon if needed.

For waterproofing, two 12-15 mil (wet) coats are recommended. When spray applying Total Lastic Premier, it is suggested that the first coat is back-rolled to achieve the best results.

Handling and Storage

Do not apply to frozen or saturated surfaces. Do not apply if precipitation is forecast within 8 hours of application. Do not apply if the temperature cannot be maintained above 40F for 24 hours. Shelf life in closed containers is 12-18 months when stored at 50-100F. Cleanup with water or soapy water before drying.

Maintenance

If Total Lastic becomes dirty or stained, clean with

a mild cleaner solution and low-pressure spray rinse. For scars or hard to clean stains, recoat with T-Wall Lastic.

Precautions

Total Lastic is an alkaline water based material. Do not ingest. Avoid contact with skin and eyes. In case of contact, flush with water. For contact with eyes, get immediate medical attention in addition to flushing. Wear safety glasses and protective clothing. Keep out of reach of children and pets.



Total Wall
888.702.9915 Phone
888.702.9916 Fax
www.totalwall.com

Technical Data

Flash point	>200 F	Seta
Density	11.8 lb/gal	
Viscosity	approx 25000 cps	
pH	9.0 - 9.8	
Elongation	500 %	ASTM D412
Actives	79.1%	ASTM D1044
Solids	53.45%	
PVC	40.0	(calculated)
Moisture Vapor		
Transmission	11 perms	ASTM E96
Pigment	Non-chalking	UV rated
Resin Chemistry	Internally plasticized acrylic emulsions	